

PEARLCOAT® 162K

Thermoplastic Polyurethane Elastomer

PEARLCOAT® 162K is a polyether based TPU, supplied in form of translucent, colourless pellets, combining hardness with excellent low temperature flexibility and very good hydrolysis resistance.

Physical Property	Test Method	Typical Values *
Density @ 20°C	DIN 53.479	1.11 g/cm ³
Shore Hardness	DIN 53.505	82 A
Tensile Strength	DIN 53.504	30 MPa
Modulus @ 100% Elongation	DIN 53.504	5 MPa
Modulus @ 300% Elongation	DIN 53.504	10 MPa
Elongation @ Break	DIN 53.504	550 %
Abrasion Loss	DIN 53.516	25 mm ³
Melting Range (MFI=10)	MQSA 111	145 – 155 °C
Tg. (DSC, 10°C / min.)	DIN 51.007	-42 °C

* These are typical values & should not be used for establishing specifications.

** Temperature at which MFI = 10 g/10 min @ 21.6 kg.

APPLICATIONS

PEARLCOAT® 162K is used in melt coatings on textile substrates, for end-uses in industrial coatings (for life-jackets, etc.) obtained by extrusion and calendaring.

PEARLCOAT® 162K is used for obtaining extruded films and fabric coatings.

WORKING INSTRUCTIONS

In accordance with our experience, the characteristics of the extruder that are suitable for processing PEARLCOAT® 162K are the following:

1. L/D ratio between 25:1 and 30:1
2. The extruder screw must have 3 zones and a compression ratio in between 2:1 and 3:1 (Usually, the screws that are used for Polyethylene extrusion give good results).
3. The extruder screw should have a continuous regulation device and a working power higher than for processing other plastics.
4. The speed of the extruder should be low (12 to 60 rpm, depending on its diameter), so as to avoid material degradation due to shearing.




PEARLCOAT® 162K

Thermoplastic Polyurethane Elastomer

5. The filters used should be disks with holes of 1.5 to 5 mm. (depending on the screw and the die), and screen packs (the number of meshes /cm² will depend on the end product that is processed), so as to create a pressure built-up.

For optimum results, previous drying of the product during 2 hours at 90-100° C is advisable, in a hot air circulatory, vacuum or desiccant-air dryer.

The suggested processing-temperature profiles for film extrusion (flat film) are depicted in the figure below.



EXTRUDER & CONDITIONS
 TYPE.- 30/25D (L/D=25:1), COOLING.- Air, SCREW.- 3:1, SPEED.- 50 rpm
 BREAKER PLATE.- --, FILTER PACK.- --, THICKNESS DIE.- 0,2 mm, PRE-DRYING.- 1h @100 °C

HEALTH AND SAFETY

A safety data sheet on **PEARLCOAT® 162K** is available, with all information related to safety.

PEARLCOAT[®] 162K

Thermoplastic Polyurethane Elastomer

The ingredients of **PEARLCOAT[®] 162K** comply with F.D.A. regulations, as described under 21 CFR, §177.2600 "Rubber Articles intended for Repeated Use" when **PEARLCOAT[®] 162K** is used in coatings and adhesives which are in contact with food.

PACKAGING

PEARLCOAT[®] 162K is packaged in heat-sealed, moisture proof multi-layer bags of 25 Kg net weight made of PE/Aluminium/PE. Bags are shipped on pallets of 750 Kg. Additionally, PE-lined cardboard gaylords of 700 Kg net weight are available.

STORAGE

Material received from Merquinsa should be inspected to assure containers are not damaged during transportation before being stored prior to use. **PEARLCOAT[®] 162K** should be kept in a cool (15-25°C) and dry environment prior to being processed. Standard practice of consuming resin on first-in first-out basis should be employed.

For more information, please feel free to contact us at www.merquinsa.com