

PEARLSTICK® 45-40/08

Linear Thermoplastic Polyurethane

PEARLSTICK® 45-40/08 is an elastic, linear, aromatic polyurethane with a very high crystallization rate and a medium thermoplasticity level.

PRODUCT SPECIFICATIONS

Supply form

: White or slightly yellowish pellets without talcum or any other antiadherents in the formulation.

(The mentioned colour differences do not affect the quality of the adhesive)

Viscosity @ 20°C

(Brookfield RVF sp.2, 20 rpm solution at 15% in MEK)

: 650 - 950 mPa.s

(MQSA N° 40 A)

PRODUCT CHARACTERISTICS

Density @ 20°C	: Approx. 1.19 g/cm ³ .
Hydroxyl number	: Approx. 0.1 %
Hydrolysis Resistance	: Good
Minimum Activation Temperature	: Approx. 45 °C.

SOLUBILITY

PEARLSTICK® 45-40/08 is soluble in acetone, methyl ethyl ketone (MEK), cyclohexanone, dimethyl formamide, tetrahydrofurane (THF). Diluting solvents such as toluene and ethyl acetate can be added.

The solvents and diluents should be water-free (max. 0.1 %), so as to avoid subsequent side reactions during crosslinking with isocyanates.

SOLUTIONS

PEARLSTICK® 45-40/08 should be dissolved in closed tanks, and the use of a variable speed agitator is advisable. The final viscosity figures can vary, depending on the stirring process and on the solvent/diluents ratios.

Please see our technical sheet on "Process for obtaining solutions based on PEARLSTICK®".

PEARLSTICK® 45-40/08
Linear Thermoplastic Polyurethane

APPLICATIONS

PEARLSTICK® 45-40/08 is used for the production of adhesives for bonding plasticized PVC to plasticized PVC or other materials such as leather, textiles, etc.

PEARLSTICK® 45-40/08 enables the production of adhesives for spray application for the automotive and other industrial uses.

The addition of a polyfunctional isocyanate improves the heat-resistance and the strength of the joints.

HEALTH AND SAFETY

A safety data sheet on **PEARLSTICK® 45-40/08** is available, with all safety information. When solutions are prepared, the usual safety practices in the handling of chemicals should be observed, i.e.: good ventilation in the working area, good skin protection and protective goggles.

PACKAGING

PE bags containing 25 kgs. n.w.
Pallets of 750 kgs. n.w.

STORAGE

PEARLSTICK® 45-40/08 should be stored in a **cool (15-25°C) and dry place**, for periods that should not exceed 6 months, in well-closed packaging.