PEARLSTICK® 48-60/19

Linear Thermoplastic Polyurethane

PEARLSTICK® 48-60/19 is an elastic, linear, aromatic polyurethane with a very high crystallization rate and a low-medium thermoplasticity level.

PRODUCT SPECIFICATIONS

Supply form	***: White or slightly yellowish pellets*** *(The mentioned colour difference does not affect the quality of the adhesive)*	
Viscosity @ 20ºC *(Brookfield RVF sp.6, 20 rpm solution at 15% in MEK)*	***: 1700 - 2200 mPa.s***	*(MQSA Nº 40 A)*

PRODUCT CHARACTERISTICS

Density @ 20ºC	: Approx. 1.19 g/cm^3.	
Hydroxyl number	: Approx. 0.1 %	
Heat Resistance	: Excellent	
Freezing Resistance	: Very good	*(MQSA Nº 90)*
Minimum Activation Temperature	: Approx. 60 ºC.	

SOLUBILITY

PEARLSTICK® 48-60/19 is soluble in Acetone, MEK, Cyclohexanone, Dimethyl formamide, Tetrahydrofurane (THF). Diluting solvents such as Toluene and Ethyl Acetate can be added.
The solvents and diluents should be water-free (max. 0.1 %), so as to avoid subsequent side reactions during crosslinking with isocyanates.

SOLUTIONS

PEARLSTICK® 48-60/19 gives transparent solutions. It they should be dissolved in closed tanks and the use of high shear equipments is advisable.
The final viscosity figures can vary, depending on the stirring process and on the solvent/diluents ratios.

Please see our technical sheet on "**Process for obtaining solutions based on PEARLSTICK®**".

Merquinsa's Products are sold subject to Merquinsa's General Sales Conditions printed on the back of invoices and other shipping documents (available upon request). This is correct information based on our experience, and is given in good faith and without compromise. Each purchaser bears full responsibility for the application, use and processing of Merquinsa's products described herein, as well as their suitability to the purchaser's specific application, as this is beyond Merquinsa's control.

Gran Vial, 17 08160 Montmeló, Spain Tel. (34) 93 572 11 00 Fax (34) 93 572 09 34
E-mail: info@merquinsa.com http://www.merquinsa.com
Registered in Barcelona Trade Register under Tax Identification Number B08530305, volume 31186, folio 106, page B-30777, entry 12.

ISO 9001 CERTIFICATED FIRM
ISO 14001 CERTIFICATED FIRM
Responsible Care®

APPLICATIONS

PEARLSTICK® 48-60/19 is used for the production of adhesives for bonding plasticized PVC to plasticized PVC or other materials such as leather, textiles, rubber, in the shoe industry. The addition of a polyfunctional isocyanate improves the performance of the adhesive.

HEALTH AND SAFETY

A safety data sheet on **PEARLSTICK® 48-60/19** is available, with all safety information. When solutions are prepared, the usual safety practices in the handling of chemicals should be observed, i.e.: good ventilation in the working area, good skin protection and protective goggles.

PACKAGING

PE bags containing 25 kg (net weight).
Pallets of 750 kg (net weight).

STORAGE

PEARLSTICK® 48-60/19 should be stored in a **cool (15-25ºC) and dry place,** for periods that should not exceed 6 months, in well-closed packaging.

Merquinsa's Products are sold subject to Merquinsa's General Sales Conditions printed on the back of invoices and other shipping documents (available upon request). This is correct information based on our experience, and is given in good faith and without compromise. Each purchaser bears full responsibility for the application, use and processing of Merquinsa's products described herein, as well as their suitability to the purchaser's specific application, as this is beyond Merquinsa's control.

Gran Vial, 17 08160 Montmeló, Spain Tel. (34) 93 572 11 00 Fax (34) 93 572 09 34
E-mail: info@merquinsa.com http://www.merquinsa.com
Registered in Barcelona Trade Register under Tax Identification Number B08530305, volume 31186, folio 106, page B-30777, entry 12.

ISO 9001 DNV CERTIFICATED FIRM
ISO 14001 DNV CERTIFICATED FIRM
Responsible Care®