PEARLTHANE® 15N95UV

Thermoplastic Polyurethane Elastomer

PEARLTHANE® 15N95UV is a polyether copolymer-based TPU, supplied in form of translucent, colorless pellets, combining hardness with excellent mechanical properties and excellent hydrolysis resistance. It can be extruded and injection-molded.

TYPICAL PROPERTIES

Property	Test Method	Typical Values *
Specific gravity	ASTM D-792	1.10 g/cm^3
Shore Hardness	ASTM D-2240	95 A / 45 D
Tensile Strength	ASTM D-412	5076 psi
Elongation @ Break	ASTM D-412	545 %
Modulus @ 100% Elongation	ASTM D-412	1450 psi
Modulus @ 300% Elongation	ASTM D-412	2755 psi
Tear Strength	ASTM D-624 (Die C)	830 lb/in
Abrasion Loss	DIN 53.516	25 mm^3
Compression Set *(70 h. @ 73ºF)*	ASTM D-395	25 %
Compression Set *(24 h. @ 158ºF)*	ASTM D-395	40 %
Moisture Content	MQSA 44	< 0.1 %
Melting Range *(MFI=10)*	MQSA 111	375 – 395 ºF
Tg *(DSC, 50ºF / min)*	DIN 51.007	- 51ºF

** These are typical values & should not be used for establishing specifications.*
*** Temperature at which MFI = 10 g/10 min @ 21.6 kg.*

WORKING INSTRUCTIONS

For optimum results, previous drying of the product during 1-2 hours at 210 - 230 ºF is advisable, in a hot air circulatory, vacuum or desiccant-air dryer.

EXTRUSION

In accordance with our experience, the characteristics of the extruder that are suitable for processing **PEARLTHANE® 15N95UV** are the following:

1. L/D ratio between 25:1 and 30:1
2. The extruder screw must have 3 zones and a compression ratio between 2:1 and 3:1. (Usually, the screws that are used for Polyethylene extrusion give good results).
3. The extruder screw should have a continuous regulation device and a working power higher than for processing other plastics.
4. The speed of the extruder should be low (12 to 60 rpm, depending on its diameter), so as to avoid material degradation due to shearing.

Issue USA 04 04/08 (Supersedes USA 03)

Merquinsa's Products are sold subject to Merquinsa's General Sales Conditions printed on the back of invoices and other shipping documents (available upon request). This is correct information based on our experience, and is given in good faith and without compromise. Each purchaser bears full responsibility for the application, use and processing of Merquinsa's products described herein, as well as their suitability to the purchaser's specific application, as this is beyond Merquinsa's control.

Gran Vial, 17 08160 Montmeló, Spain Tel. (34) 93 572 11 00 Fax (34) 93 572 09 34
E-mail: info@merquinsa.com http://www.merquinsa.com
Registered in Barcelona Trade Register under Tax Identification Number B08530305, volume 31186, folio 106, page B-30777, entry 12.

ISO 9001 CERTIFICATED FIRM
ISO 14001 CERTIFICATED FIRM
Responsible Care®

5. The filters used should be disks with holes of $^{1}/_{16}$ to $^{3}/_{16}$ in (depending on the screw and the die), and screen packs (the no. of meshes /in^{2} will depend on the end product which is processed), so as to create a pressure built-up.

The suggested processing-temperature profiles for film extrusion (flat film) are depicted in the figure below:



	1	2	3	4	DIE
PROFILE 15N95UV/1	365	390	410	390	370
PROFILE 15N95UV/2	390	445	445	430	385

EXTRUDER & CONDITIONS
TYPE.- 30/25D (L/D=25:1), COOLING.- Air, SCREW.- 3:1, SPEED.- 25-50 rpm.,
BREAKER PLATE.- --, FILTER PACK.- --, THICKNESS DIE.- 0,2 mm, PRE-DRYING.- 1h @ 220 ºF

INJECTION MOLDING

Based on an injection molding equipment with the following characteristics:

Closing force:	: 30 tons
Screw diameter:	: 1.02 in
L/D ratio:	: 23
Maximum hydraulic pressure:	: 3050 psi.
Mold:	: Plaque 4.7x4.7x0.08 in.

Issue USA 04 04/08 (Supersedes USA 03)

Merquinsa's Products are sold subject to Merquinsa's General Sales Conditions printed on the back of invoices and other shipping documents (available upon request). This is correct information based on our experience, and is given in good faith and without compromise. Each purchaser bears full responsibility for the application, use and processing of Merquinsa's products described herein, as well as their suitability to the purchaser's specific application, as this is beyond Merquinsa's control.

Gran Vial, 17 08160 Montmeló, Spain Tel. (34) 93 572 11 00 Fax (34) 93 572 09 34
E-mail: info@merquinsa.com http://www.merquinsa.com
Registered in Barcelona Trade Register under Tax Identification Number B08530305, volume 31186, folio 106, page B-30777, entry 12.

ISO 9001 CERTIFICATED FIRM
ISO 14001 CERTIFICATED FIRM
Responsible Care®

The suggested processing conditions are as follows:

INJECTION CONDITIONS

Feed zone	385ºF	Injection pressure	1590 psi
Compression zone	390ºF	Injection time	2.5 sec
Metering zone	390ºF	Holding pressure	870 psi
Nozzle	390ºF	Holding time	15 sec
Mold temperature	95ºF	Cooling time	38 sec

Screw speed : approx. 75 rpm.

APPLICATIONS

PEARLTHANE® 15N95UV can be used for high performance animal ear tags and a variety of technical parts for outdoor use. When extruded**,** it can be used for tubing and profiles.

To improve the microbiological protection of **PEARLTHANE® 15N95UV**, it is necessary to add a biocide, preferably in form of TPU-based masterbatch.

HEALTH AND SAFETY

A safety data sheet on **PEARLTHANE® 15N95UV** is available, with all information related to safety.

PACKAGING

PEARLTHANE® 15N95UV is packaged in heat-sealed, moisture proof multi–layer bags of 25 kg net weight made of PE/Aluminium/PE. Bags are shipped on pallets of 750 kg. Additionally, PE-lined cardboard gaylords of 700 kg net weight are available.

STORAGE

Material received from Merquinsa should be inspected to assure the containers are not damaged during transportation before being stored prior to use. **PEARLTHANE® 15N95UV** should be kept in a cool (60-75ºF) and dry environment prior to being processed. Standard practice of consuming resin on first-in first-out basis should be employed.

For more information, please feel free to contact us at **www.merquinsa.com**

Issue USA 04 04/08 (Supersedes USA 03)

Merquinsa's Products are sold subject to Merquinsa's General Sales Conditions printed on the back of invoices and other shipping documents (available upon request). This is correct information based on our experience, and is given in good faith and without compromise. Each purchaser bears full responsibility for the application, use and processing of Merquinsa's products described herein, as well as their suitability to the purchaser's specific application, as this is beyond Merquinsa's control.

Gran Vial, 17 08160 Montmeló, Spain Tel. (34) 93 572 11 00 Fax (34) 93 572 09 34
E-mail: info@merquinsa.com http://www.merquinsa.com
Registered in Barcelona Trade Register under Tax Identification Number B08530305, volume 31186, folio 106, page B-30777, entry 12.

ISO 9001 CERTIFICATED FIRM
ISO 14001 CERTIFICATED FIRM
Responsible Care®